

CMV Engineering, LLC

5751 Greenton Way
St. Louis, Missouri 63128
Telephone: 314-807-8149
E-Mail: cvogt@att.net

May 30, 2017

Tapawingo Subdivision
c/o Jeff Sanders
6 Break Ct.
Sunset Hills, Mo. 63127

Project: Tapawingo Streets
Concrete Coring Report


Dear Mr. Sanders,

Attached are the results of the concrete slab coring of 25 random locations in the Tapawingo Subdivision.

The average thickness is 7.37" with the highest at 8.25" and the lowest 6.25". The field technicians reported that the concrete slabs had an approximate 4" granular base. No tests were performed to locate steel dowel bars. According to trustees of the subdivisions, bars have been evident during removal and replacement of concrete slabs.

If you have any questions, please don't hesitate to contact our office.

Sincerely,



Carl M. Vogt, P.E.
CMV Engineering, LLC

TAPAWINGO STREETS

CORING RESULTS

<u>CORE</u>	<u>LENGTH IN INCHES</u>
1	7.625
2	7.875
3	7.750
4	7.750
5	8.000
6	8.000
7	6.875
8	6.750
9	7.000
10	7.875
11	7.125
12	6.875
13	7.500
14	7.625
15	7.125
16	7.125
17	7.000
18	8.500
19	6.375
20	7.500
21	6.625
22	6.250
23	7.000
24	8.250
25	7.875

AVERAGE THICKNESS 7.370"

HIGHEST 8.50"
LOWEST 6.25"